

# Paint Formulation Number 5

## Colored Paints

### Application

For use on many types of wood and metal surfaces where an attractive and high performance protective coating is required.

### Properties

Durable, chemical and corrosion resistant coatings. Excellent weatherability characteristics. Easily applied by brush, roller or spray.

#### Formulation/Method of Manufacture

	Red	Gray	Tan
Medium Oil Varnish*	82%	75%	85%
Red Iron Oxide	18%	--	--
Titanium Dioxide	--	25%	8%
Yellow Iron Oxide	--	--	7%

1. Sandmill 50% of varnish with pigment to correct grind (NS 7 Hegman Grind). Then blend in remainder of varnish.
2. Cold blend.

\* See [Medium Oil Varnish - Linseed/Tung/Gilsonite Resin Blend](#)

C-200-0892